



(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 191 116 A1

(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:

27.03.2002 Bulletin 2002/13

(51) Int Cl.7: **C22C 38/18, C21D 1/18**(21) Application number: **01930356.9**

(86) International application number:

PCT/RU01/00172(22) Date of filing: **24.04.2001**

(87) International publication number:

WO 01/81644 (01.11.2001 Gazette 2001/44)

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**

Designated Extension States:

AL LT LV MK RO SI(30) Priority: **25.04.2000 RU 2000110329**(71) Applicant: **Institut Metallurgii i Materialovedeniya
Imeni A.A. Baikova Rossiiskoi Akademii Nauk
Moscow, 117911 (RU)**

(72) Inventors:

- **BANNYKH, Oleg Alexandrovich
Moscow, 117335 (RU)**
- **BLINOV, Viktor Mikhailovich
Moscow, 113303 (RU)**

- **KOSTINA, Mariya Vladimirovna
Moscow, 125499 (RU)**
- **MALYSHEVSKY, Viktor Andreevich
St.Petersburg, 195253 (RU)**
- **RASHEV, Tsolo Vylkovich
Sofia (BG)**
- **KALININ, Grigory Yurievich
St.Petersburg, 194358 (RU)**
- **RIGINA, Ljudmila Georgievna
Moscow, 117296 (RU)**
- **DYMOV, Alexei Viktorovich
Moscow, 109144 (RU)**
- **USTINOVSHIKOV, Yury Ivanovich
Izhevsk, 426000 (RU)**

(74) Representative: **Tergau & Pohl Patentanwälte
Mögeldorf Hauptstrasse 51
90482 Nürnberg (DE)**(54) **AUSTENIC STEEL**

(57) Austenitic steel contains from 0.01 to 0.04% by weight of carbon, from 21.00 to 24.00% by weight of chromium, from 0.25 to 0.65% by weight of silicon, from 0.25 to 0.70% by weight of manganese, from 1.00 to 1.40% by weight of nitrogen, the balance being iron, the total content of ferrite-forming components in the steel, namely, of silicon and chromium, and the total content of austenite-forming components therein, namely, of carbon, nitrogen and manganese, obeying the following

condition:

$$\frac{0.48[\text{Si}]+[\text{Cr}]}{30[\text{C}]+18[\text{N}]+0.01[\text{Mn}]} = \text{from } 0.8 \text{ to } 1.3,$$

where [Si], [Cr], [C], [N], [Mn] is the content in the steel of silicon, chromium, carbon, nitrogen, and manganese, respectively, expressed in % by weight.

Description**Field of the Art**

[0001] The present invention relates to the field of metallurgy, and more particularly to corrosion-resistant and wear-resistant steel.

Prior Art

[0002] Various kinds of steel are known in the art, that are used in the manufacture of products related to medical engineering, e.g., prostheses, implants, medical tools, and the like. Steels used for the indicated purpose must meet definite requirements both from the standpoint of the interaction of products made from such steels with human organism and from the standpoint of the physico-mechanical characteristics thereof.

[0003] However, the strength and wear-resistance of the known steels used for medical purposes are not sufficient, and therefore prostheses, implants, and medical tools manufactured from the known steels cannot insure the required safety and reliability in the course of their operation and rapidly wear out. In the case of prolonged contact with human tissues the known steels used for medical purposes induce allergic reactions of human organism.

[0004] To the category of steels used for medical purposes there belong corrosion-resistant austenitic steels described in the International Translator of Modern Steels and Alloys (Prof. V.S.Kershenbaum (Ed.), "International Engineering Encyclopedia" Series, Moscow, 1992 (in Russian)), for instance, steel grade AISI 316H (USA), containing 0.04-0.10% by weight of carbon, 16.0-18.0% by weight of chromium, 10.0-14.0% by weight of nickel, 2.0-3.0% by weight of molybdenum, 1.0% by weight or less of silicon, 2.0% by weight or less of manganese, 0.03% by weight or less of sulfur, the balance being iron, or steel grade DIN 17440 (DE), containing not more than 0.1% by weight of carbon, not more than 1.0% by weight of silicon, not more than 2.0% by weight of manganese, not more than 0.045% by weight of phosphorus, not more than 0.03% by weight of sulfur, 16.5-18.5% by weight of chromium, 12.0-14.0% by weight of nickel, less than 5.0% by weight of titanium and 2.0-3.0% by weight of molybdenum.

[0005] Said steels have a single-phase austenitic structure, but they contain an appreciable amount of critical and costly nickel which, among other things, may induce allergic reactions in human organism when said steels are used for medical purposes; furthermore, said steels contain manganese which reacts with human blood.

[0006] Besides, said steels have a low strength (σ_B being less than 520 MPa, $\sigma_{0.2}$ being less than 250 MPa) and an insufficient wear-resistance, so that they fail to meet the requirements to the materials for products to be used in medical engineering.

[0007] Closest in its chemical composition to the steel of the present invention is the corrosion-resistant steel described in EP No. 0123054, 06.05.1987. This steel contains, in % by weight: carbon, from 0.01 to 0.5; chromium, from 3.0 to 45.0; niobium, up to 10.0; silicon, up to 2.0; manganese, up to 0.10; molybdenum, up to 10.0; vanadium, up to 5.0; titanium, niobium and/or tantalum, up to 2.0; cerium, up to 1.0; aluminum, up to 0.3; nitrogen, from 0.2 to 5.0; iron, the balance.

[0008] Said steel has an austenitic-ferritic structure and is magnetizable. At 400°C said steel has the yield point $R_{p0.2}(\sigma_{0.2})$ less than 400 N/mm² and at 600°C it has the yield point $R_{p0.2}(\sigma_{0.2})$ less than 250 N/mm². The described steel is intended, owing to its heat resistance, for manufacturing gas and steam turbines.

[0009] The above-indicated steel is not suitable for manufacturing products to be used in medical engineering, because, in the first place, its structure comprises at least 50% of ferromagnetic components able to react with human blood containing iron ions; in the second place, said steel contains manganese and nickel which induce allergic reactions when in contact with human tissues.

Disclosure of the Invention

[0010] The present invention is directed to the provision of a nonmagnetic steel which has a high mechanical strength, high corrosion and wear resistance, plasticity and is inactive with respect to human tissues.

[0011] Said object is accomplished in the provision of a steel containing carbon, chromium, silicon, manganese, nitrogen and iron, which steel, according to the invention, contains said components in the following relationship, % by weight:

carbon	from 0.01 to 0.04
chromium	from 21.00 to 24.00
silicon	from 0.25 to 0.65
manganese	from 0.25 to 0.70

(continued)

nitrogen	from 1.00 to 1.40
iron	the balance,

the total content of ferrite-forming components in the steel, namely, of silicon and chromium, and the total content of austenite-forming components therein, namely, of carbon, nitrogen and manganese, obeying the following condition:

$$\frac{0.48[\text{Si}]+[\text{Cr}]}{30[\text{C}]+18[\text{N}]+0.01[\text{Mn}]} = \text{from } 0.8 \text{ to } 1.3,$$

where [Si], [Cr], [C], [N], [Mn] is the content in the steel of silicon, chromium, carbon, nitrogen, and manganese, respectively, expressed in % by weight.

[0012] According to the invention, the proposed steel has a single-phase austenitic structure, the yield point $\sigma_{0.2}$ from 700 to 900 MPa, the breaking point σ_B from 1100 to 1250 MPa, obtained after water quenching at a temperature of from 1190 to 1230°C or obtained after water quenching at a temperature of from 1190 to 1230°C and subsequent tempering at a temperature of from 400 to 430°C for 3 to 3.5 hours with subsequent cooling in air.

[0013] Owing to the invention, the claimed nonmagnetic steel having a single-phase structure possesses a high mechanical strength, high corrosion- and wear-resistance, plasticity, and is inactive with respect to human tissues.

[0014] Further objects and advantages of the claimed invention will become clear from the following detailed description of the proposed austenitic steel and examples of its particular composition.

[0015] A nonmagnetic steel with the single-phase austenitic structure has been developed, that has a high mechanical strength, plasticity, corrosion- and wear-resistance, suitable for the manufacture of products to be used in medical engineering, for instance, prostheses, implants, medical tools, and the like.

The Best Mode for Carrying out the Invention

[0016] The steel claimed in the present invention contains from 0.01 to 0.04% by weight of carbon, from 21.00 to 24.00% by weight of chromium, from 0.25 to 0.65% by weight of silicon, from 0.25 to 0.70% by weight of manganese, from 1.00 to 1.40% by weight of nitrogen, the balance being iron, the total content of ferrite-forming components in the steel, namely, of silicon and chromium, and the total content of austenite-forming components therein, namely, of carbon, nitrogen and manganese, obeying the following condition:

$$\frac{0.48[\text{Si}]+[\text{Cr}]}{30[\text{C}]+18[\text{N}]+0.01[\text{Mn}]} = \text{from } 0.8 \text{ to } 1.3,$$

where [Si], [Cr], [C], [N], [Mn] is the content in the steel of silicon, chromium, carbon, nitrogen, and manganese, respectively, expressed in % by weight.

[0017] The results of our investigations have shown that with the content of nitrogen in the steel less than 1.0% by weight, homogeneous γ -solid solution (austenite) cannot be obtained in its structure, whereas with the content of nitrogen exceeding the claimed 1.4% by weight the conditions of melting and working the steel become complicated; the presence of nitrogen in the specified amount makes it possible to increase the yield point of the steel by as much as 2 to 3 times and to rule out introducing nickel and manganese, added heretofore to steel for these purposes, these additives inducing allergic reactions when in contact with human tissues. The content of chromium in the claimed amount of from 21.00 to 24.00% by weight increases the corrosion resistance of the steel, and under the indicated melting conditions the solubility of nitrogen can be increased eight-fold. It is difficult to attain the content of carbon in the steel less than the claimed 0.01 % by weight without additional metallurgical operations, which make the steel appreciably more expensive; with the content of carbon exceeding the claimed 0.04% by weight the conditions, the conditions of formation of the homogeneous structure of nitrogen austenite are substantially complicated by the process of separation of large particles of chromium carbide of Cr_{23}C_6 type along the grain boundaries or of the formation of carbonitrides which lead to lowering the plasticity of steel and its resistance to intercrystallite corrosion. The content of chromium less than the claimed 21.00% by weight complicates the conditions of melting the steel with the claimed nitrogen content, which, as it was indicated, ranges from 1.00 to 1.40% by weight and insures the attainment, after tempering, of a homogeneous austenitic structure of steel containing no δ -ferrite or α -martensite ferromagnetic phases; with the content of chromium exceeding the claimed 24% by weight, the δ -phase and nitrides appear in the steel structure, which deteriorate the mechanical properties of steel and are soluble only at temperatures that are technically difficult to achieve.

[0018] Our investigations have shown that for obtaining stable austenitic structure of the claimed steel the ratio of the sum of ferrite-forming components, namely, of silicon and chromium, to austenite-forming components, namely, carbon, nitrogen and manganese, is also of importance. So, it was found that when

$$\frac{0.48[\text{Si}]+[\text{Cr}]}{30[\text{C}]+18[\text{N}]+0.01[\text{Mn}]} < 0.8,$$

a completely austenitic structure of steel cannot be obtained, while in the case of

$$\frac{0.48[\text{Si}]+[\text{Cr}]}{30[\text{C}]+18[\text{N}]+0.01[\text{Mn}]} > 1.3$$

δ -ferrite appears in the steel structure.

[0019] Water quenching at a temperature of 1190-1230°C is sufficient for the homogenization of the γ -solid solution - at a temperature above 1230°C grain growth and the appearance of δ -ferrite are observed; at a temperature lower than 1190°C complete dissolution of nitrides which deteriorate the viscosity and plasticity of steel cannot be attained. Tempering from the temperature of 430°C for 3-3.5 hours does not lead to the decomposition and nitrogen depletion of austenite. At a temperature not exceeding 400°C the strength of steel is not impaired. Keeping for 3-3.5 hours is sufficient for ensuring homogeneity of the steel structure.

[0020] The austenitic steel claimed in the present invention has high physico-mechanical characteristics: the yield point ($\sigma_{0.2}$) is 700-900 MPa, the breaking point (σ_B) is 1100-1250 MPa, a considerable abrasive resistance at an elevated plasticity: δ is 28-51%, ψ is 20.5-39.0%. Said characteristics provide an increased service life and reliability of constructions and products from such steel, including implants subject to high loads, for instance, coxofemoral endoprotheses.

[0021] The claimed steel is advantageous over the prior art in that the content of carbon which contributes to the formation of thrombi is minimized, nickel which may induce allergic reactions and eczema is absent, and the steel is non-magnetic (because ferromagnetic material actively reacts with blood containing iron ions).

[0022] Therefore, the claimed austenitic steel can be used as a highly strong, wear- and corrosion-resistant non-magnetic material in the manufacture of products related to medical engineering, e.g., prostheses, implants, medical tools, and the like, providing for shortening the postoperative period of patients, ruling out the origination of inflammatory processes.

[0023] The claimed steel will also find successful application in instrument-making, power plant engineering, diesel building, cryogenic technology.

[0024] For a better understanding of the present invention, examples of its particular embodiment are given hereinbelow.

Example

[0025] The melting of austenitic steel was carried out in an induction furnace under 22 atm pressure of gaseous nitrogen (melts 1-4, where melt 1 corresponded to the steel described in EP 123054 and melts 2-4 corresponded to the steel claimed in the present invention). For determining the mechanical properties of the steel obtained in melts 1-4 and its resistance to intercrystallite corrosion after heat treatment, the following samples were forged at 1200°C: 13x13 mm rods (melt 1, 2.1, 2.2, 3, 4); a large-size sample from which a 50x50 mm fragment was cut out (melt 2.3), on which the mechanical properties of the steel and its resistance to intercrystallite corrosion were determined.

[0026] The amount of austenite and martensite in the steel obtained in melts 1-4 was determined on an x-ray diffractometer. Mechanical elongation tests were carried out with elongation rate of 1 mm/min on cylindrical samples with the 5 mm diameter of the working surface. Resistance to intercrystallite corrosion was determined by the method of potentiodynamic reactivation in an electrolyte (mole/liter) - 0.5 H₂SO₄ + 0.01 KSCN - with polarization from minus 0.5 to plus 0.3 V with the scanning rate of 2.5x10⁻³ V/sec. The measure of alloy resistance to intercrystallite corrosion was assumed to be the ratio (K) of the reactivation charge to the passivation charge.

[0027] Comparative tests of the claimed steel (melts 3, 4) and of the known steel A128MB2 (International Translator of Modern Steels and Alloys (Prof. V.S. Kershenbaum (Ed.), "International Engineering Encyclopedia" Series, Moscow, 1992 (in Russian)) for wear resistance using a secured abrasive were carried out on a laboratory setup. The samples performed back-and-forth motion with their end face part against a polishing paper on a corundum base after breaking-in under similar conditions. The length of one working stroke of the samples was 0.13 meter, the sample friction path per test with the rate of movement equal to 0.158 m/sec was 78 meters. The transverse displacement of the polishing paper per double stroke of the sample was 0.0012 meter. Normal load on the sample was 98 N (specific load was 100 MPa). The adopted test conditions insured insignificant heating of the working surface of the samples. Before and after

testing the samples were weighed on an analytical balance with the scale division value of 0.1 mg. The relative wear-resistance in abrasive wear was determined as an arithmetic mean of the results of two parallel tests, using the formula:

$$\varepsilon = \frac{M_r}{M_t}, \text{ where } M_r \text{ is the absolute mass wear of the reference sample, g;}$$

$$M_t \text{ is the absolute mass wear of the test sample, g.}$$

[0028] A sample of steel grade A128B2, widely used as a wear-resistant material for products and constructions subject to high loads, after tempering at 1100°C with water quenching, was adopted as the reference sample.

[0029] Tables 1, 2 and 3 that follow show the chemical composition of the melted steel, % by weight (Table 1); the mechanical properties and resistance of steel whose chemical composition is shown in Table 1, to intercrystallite corrosion after heat treatment (Table 2); the results of testing for wear the steel whose composition is shown in Table 1 (Table 3).

Table 1

Melt No.	C	N	Cr	Mn	Si	Ni	Mo	Q*
1	0.0	0.51	13.0	1.05	0.50	2.90	3.50	1.32
2	0.02	1.02	21.45	0.19	0.42	-	-	1.13
3	0.02	1.281	21.44	0.22	0.40	-	-	0.96
4	0.03	1.29	23.85	0.22	0.45	-	-	0.99

$$Q^* = \frac{0.48[\text{Si}] + [\text{Cr}]}{30[\text{C}] + 18[\text{N}] + 0.01[\text{Mn}]}$$

Table 2

Melt No.	Heat treatment	σ_B , MPa	$\sigma_{0.2}$, MPa	δ , %	ψ , %	K*
1	Annealing 950°C + tempering 650°C	820	600	22	-	0.11
2.1	Hardening 1200°C	1250	860	28	24	0.10
2.2	Annealing 1200°C + tempering 400°C, 3 hours	1250	900	29.5	22.5	0.10
2.3	Annealing 1200°C + tempering 400°C, 3 hours	1100	700	23	25	0.10
3	Annealing 1200°C + tempering 400°C, 3 hours	1250	895	29	20.5	0.10
4	Annealing 1200°C + tempering 400°C, 3 hours	1250	815	51.0	39.0	0.09

at $K^* < 0.11$ the alloy is not liable to intercrystallite corrosion.

Table 3

Melt No.	Heat treatment	Relative wear-resistance, ε
3	Annealing 1200°C	1.23
4	Annealing 1200°C + tempering 400°C, 3 hours	1.06
4	Annealing 1200°C	1.40
4	Annealing 1200°C + tempering 400°C, 3 hours	1.32
Steel A128MB2	Annealing 1200°C	1 (reference sample)
	Annealing 1200°C + tempering 400°C, 3 hours	0.95

Industrial Applicability

[0030] The claimed austenitic steel will find application in the manufacture of products related to medical engineering, e.g., prostheses, implants, medical tools, and the like, insuring shortening of the postoperative period of patients, ruling out the origination of inflammatory processes; the claimed steel will also find successful application in instrument-making, power plant engineering, diesel building, cryogenic technology.

Claims

1. Steel containing carbon, chromium, silicon, manganese, nitrogen and iron, **wherein** said steel contains said components in the following relationship, % by weight:

carbon	from 0.01 to 0.04
chromium	from 21.00 to 24.00
silicon	from 0.25 to 0.65
manganese	from 0.25 to 0.70
nitrogen	from 1.00 to 1.40
iron	the balance,

the total content of ferrite-forming components in the steel, namely, of silicon and chromium, and the total content of austenite-forming components therein, namely, of carbon, nitrogen and manganese, obeying the following condition:

$$\frac{0.48[\text{Si}] + [\text{Cr}]}{30[\text{C}] + 18[\text{N}] + 0.01[\text{Mn}]} = \text{from } 0.8 \text{ to } 1.3,$$

where [Si], [Cr], [C], [N], [Mn] is the content in the steel of silicon, chromium, carbon, nitrogen, and manganese, respectively, expressed in % by weight.

2. Steel according to claim 1, **wherein** said steel has a single-phase austenitic structure, the yield point $\sigma_{0.2}$ from 700 to 900 MPa, the breaking point σ_B from 1100 to 1250 MPa.
3. Steel according to claim 1, **wherein** said steel has a single-phase structure obtained after water quenching at a temperature of from 1190 to 1230°C.
4. Steel according to claim 1, **wherein** said steel has a single-phase structure obtained after water quenching at a temperature of from 1190 to 1230°C and subsequent tempering at a temperature of from 400 to 430°C for 3 to 3.5 hours with subsequent cooling in air.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/RU 01/00172

A. CLASSIFICATION OF SUBJECT MATTER: IPC ⁷ C22C 38/18, C21D 1/18 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC ⁷ C22C 38/00, 38/18, C21D 1/00, 1/18 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0123054 A1 (FRIED.KRUPP GESELLSCHAFT MIT BESCHRANKTER HAFTUNG) 31 October 1984 (31.10.84)	1, 3-4
A	RU 2092606 C1 FIZIKO-TECHNICHESKY INSTITUT URALSKOGO OTDELENYA RAN) 10 October 1997 (10.10.97)	1, 2
A	SU 1719456 A1 (DNEPROPETROVSKY METALLURGICHESKY INSTITUT) 15 March 1992 (15.03.92)	1-4
A	US 5405575 A (KAWASAKI STEEL CORPORATION) 11 April 1995 (11.04.95)	1-4
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search 20 August 2001 (20.08.01)		Date of mailing of the international search report 6 September 2001 (06.09.01)
Name and mailing address of the ISA/ RU Facsimile No.		Authorized officer Telephone No.